

# **Cement Mill Test Report**

Date of Issue: January 13, 2021

Plant: Product: Mill Test Report Number: Manufactured:

Exshaw, AB Portland Cement Type III MTR-III-2020-12 December 2020

## ASTM C 150-19 and AASHTO M 85-17 Standard Requirements

CHEMICAL ANALYSIS			PHYSICAL ANALYSIS			
Item	Spec limit	Test Result	Item	Spec limit	Test Re	sult
Rapid Method, X-Ray (C114)	)		Air content of mortar (%) (C185)	12 max	7	
SiO <sub>2</sub> (%)		20.1				
Al <sub>2</sub> O <sub>3</sub> (%)		4.0	Blaine Fineness (m <sup>2</sup> /kg) (C204)		631	
Fe <sub>2</sub> O <sub>3</sub> (%)		3.7				
CaO (%)		61.9	Passing 45 μm (%) (C430)		99.2	
MgO (%)	6.0 max	4.7				
SO <sub>3</sub> (%)	3.5 max	3.3	Autoclave Expansion (%) (C151)	0.80 max	0.02	
Loss on Ignition (%)	3.5 max	1.4				
Insoluble Residue (%)	1.5 max	0.19	Compressive strength (MPa, [psi]) (C109)			
CO <sub>2</sub> (%)		0.5	1 day	12.0 [1740] min	29.7	[4310]
Limestone (%)	5.0 max	1.2	3 days	24.0 [3480] min	35.9	[5210]
CaCO <sub>3</sub> in Limestone (%)	70 min	96	28 days (Reflects previous month's data)		47.9	[6940]
Inorganic Process Addition	5.0 max	-				
(Lafarge Cement Kiln Dust)						
			Time of setting (minutes)			
Adjusted Potential Phase Composition (C150)			Vicat Initial <i>(C191)</i>	45 - 375	88	
C <sub>3</sub> S (%)		55				
C <sub>2</sub> S (%)		16				
C <sub>3</sub> A (%)	15 max	4				
C₄AF (%)		11				
ASTM C 150-17 and AASHTC	O M 85-17 Optior	al Chemical Require	ments:			
NaEq (%)	0.60 max	0.57				

We certify that the above described cement, at the time of shipment, meets the chemical and physical requirements of ASTM C 150-19 & AASHTO M 85-17 STANDARD SPECIFICATIONS FOR TYPE III CEMENT; and ASTM C 150-17 & AASHTO M 85-17 OPTIONAL CHEMICAL REQUIREMENTS FOR TYPE III LOW ALKALI CEMENT.

Certified By:

Lorraine Richards

Western Canada BU - Exshaw Plant P.O. Box 160, Highway 1A, Exshaw AB, TOL 2C0 Phone: 403-673-3815

Lorraine Richards Quality Control Coordinator



# **Cement Mill Test Report**

Date of Issue: January 13, 2021

Plant: Product: Mill Test Report Number: Manufactured: Exshaw, AB Portland Cement Type III MTR-III-2020-12 December 2020

### Additional ASTM C 150-19 and AASHTO M 85-17 Standard data

#### **Additional Data**

Item	Test Result		
	Limestone	Inorganic Process Addition	
		Lafarge Cement Kiln Dust	
Amount (%)	1.2	-	
SiO <sub>2</sub> (%)	1.4	n/a	
Al <sub>2</sub> O <sub>3</sub> (%)	0.8	n/a	
Fe <sub>2</sub> O <sub>3</sub> (%)	0.3	n/a	
CaO (%)	51.5	n/a	
SO <sub>3</sub> (%)	0.2	n/a	
CO <sub>2</sub> (%)	42.2	n/a	

#### **Base Cement Phase Composition**

Item	Test Result
C <sub>3</sub> S (%)	56
C <sub>2</sub> S (%)	16
C <sub>3</sub> A (%)	4
C₄AF (%)	11

We certify that the data above reflects the materials used in cement manufacture during the production period indicated.

Note: Specifc Gravity for Portland Cements is 3.15

Certified By:

Lorraine Richards

Western Canada BU - Exshaw Plant P.O. Box 160, Highway 1A, Exshaw AB, TOL 2C0 Phone: 403-673-3815

Lorraine Richards Quality Control Coordinator