

Mill Test Report Number: SEA_NEWCEM_APRIL2021

YEAR: 2021 MONTH: MARCH PLANT: Seattle

CEMENT TYPE: NewCem Grade 100

Reference Cement					
Fineness by Air Permeability (m²/kg; ASTM C204)	395				
Fineness by 45 µm (No. 325) Sieve (% retain; ASTM C430)	1.96				
Compressive Strength					
(ASTM C109/C109 M)	<u>psi</u>	Min Limit			
7-day 28-day	5,100 6,095	5,000			
	Actual	Limits			
Total Alkalies (Na ₂ O + 0.658 K ₂ O)	0.88	0.6-0.9			
(%, ASTM C114)					

Slag	
CHEMICAL ANALYSIS	Percent
Silica Dioxide (SiO _{2;} ASTM C114)	32.3
Ferric Oxide (Fe ₂ O _{3;} ASTM C114)	0.9
Aluminum Oxide (Al ₂ O ₃ ; ASTM C114)	14.4
Calcium Oxide (CaO; ASTM C114)	43.5
Sulfur Trioxide (SO ₃ ; ASTM C114)	4.9
Magnesium Oxide (MgO; ASTM C114)	4.1
Potassium Oxide (K ₂ O; ASTM C114)	0.5
Titanium Oxide (TiO ₂ , ASTM C114)	0.5
Loss on Ignition (L.O.I.; ASTM C114)	0.42
Total Alkalies	0.57
Inorganic Process Addition	4

	Slag		
Fineness by Air Permeability (m²/kg; ASTM C204)	413		
Fineness by 45 µm (No. 325) Sieve (% retain; ASTM C430)	7.2		
Compressive Strength (ASTM C109/C109 M)	psi [Mpa]	<u>SAI</u>	SAI Limit <u>Min</u>
28-day (Previous Month)	6250 [43.1]	103	95
Specific Gravity (Mg/m³; ASTM C188)	2.87		
	<u>Actual</u>	Max	c Limit
Air Content of Mortar (%, ASTM C185)	5.6		12
Sulfide Sulfur	0.8	2.5	
(% S, ASTM C114)			
Sulfate Ion (% as SO3, ASTM C114)	2.9	A	
Autoclave expansion (%, CSA A3004-B5)	-0.005		0.5
Color Value L*	76.7		

The ground granulated blast furnace slag complies with the current specification of the chemical physical requirement of ASTM C-989, AASHTO M-302 for grade 100 Ground Granulated Blast Furace Slag (GGBFS) and and CSA A3001 Slag.

Slag source is JFE Mineral Company in Kurashiki City, Japan. NewCem is ground and manufactured in Seattle, WA.

Certified to NSF/ANSI 61

Certified by:

Daniel Waldron

Quality Control Laboratory Supervisor

April 14, 2021

A Not Applicable.