



Certified to
NSF/ANSI/CAN 61

Cement Mill Test Report

Month of Issue: MAY 2021

Plant:	Richmond, British Columbia
Product:	Portland Cement Type I/II
Mill Test Report #	R-TI-21-05
Manufactured:	APRIL 2021

ASTM C 150-20 and AASHTO M 85-20 Standard Requirements

CHEMICAL ANALYSIS			PHYSICAL ANALYSIS		
Item	Spec limit	Test Result	Item	Spec limit	Test Result
Rapid Method, X-Ray (C 114)			Air content of mortar (%) (C 185)		
SiO ₂ (%)	---	19.7		12 max	5.4
Al ₂ O ₃ (%)	6.0 max	4.8	Blaine Fineness (m²/kg) (C 204)***		
Fe ₂ O ₃ (%)	6.0 max	3.3		260 - 430	404
CaO (%)	---	63.7	Passing 45 um (%) (C 430)		
MgO (%)	6.0 max	0.9		72 min	98.5
SO ₃ (%)	3.0 max*	3.0	Autoclave expansion (%) (C 151)		
Loss on ignition (%)	3.5 max	2.9		0.80 max	0.01
Insoluble residue (%)	1.5 max	0.1	Compressive strength (MPa, [PSI]) (C 109)		
CO ₂ (%)	---	2.0			<u>Mpa</u> <u>PSI</u>
Limestone (%)	5.0 max	4.6	3 days	12.0 [1740] min	30.8 4470
CaCO ₃ in Limestone (%)	70 min	97	7 days	19.0 [2760] min	38.2 5530
Adjusted Potential Phase Composition (C 150)			28 days (Reflects previous month's data)	28.0 [4060] min	46.1 6690
C ₃ S (%)	---	55	Time of setting (minutes)		
C ₂ S (%)	---	15	Vicat Initial (C 191)		
C ₃ A (%)	8 max	7		45 - 375	98
C ₄ AF (%)	---	10	False Set (%) (C451)		
C ₃ S+4.75*C ₃ A (%)	100 max	88		50 min	86
			Heat of Hydration (C186)** - 28 day (Kj/Kg)		
			399		
			Colour (L*)		
			58		
			Mortar Bar Expansion (%) (C 1038)**		
			0.020 max 0.002		

ASTM C 150 and AASHTO M 85 Optional Chemical Requirements:

NaEq (Alkali) (%)	0.60 max	0.52
-------------------	----------	------

* May exceed 3.0% SO₃ maximum based on our C 1038 results of <0.02% expansion at 14 days.

** Current Production run not available - most recent provided, *** Maximum Blaine can be exceeded if C₃S + 4.75*C₃A(%) meets limit

Note: Specific gravity for Portland cement is considered to be 3.15

We certify that the above described cement, at the time of shipment, meets the chemical and physical requirements of applicable DOT Specifications for Type I and Type II;

ASTM C 150-20 & AASHTO M 85-20 STANDARD SPECIFICATIONS FOR TYPE I AND TYPE II CEMENT;

ASTM C 150-20 & AASHTO M 85-20 OPTIONAL CHEMICAL REQUIREMENTS FOR TYPES I & II LOW ALKALI CEMENT.

Cement complies with NSF 61

Western BU - Richmond
7611 No 9 Rd Richmond, BC
604 244 4300

Questions or enquiries can be directed to Rob Shogren

Rob Shogren, PhD
Lafarge - Technical Director
5400 W Marginal Way SW, Seattle WA
P +1 206 923 9953
E Rob.Shogren@lafargeholcim.com

Certified By:

Harold Ptachyk B.Sc., PChem
Quality Manager
5/10/2021