



Certified to
NSF/ANSI/CAN 61

Cement Mill Test Report

Month of Issue: AUGUST 2021

Plant: **Richmond, British Columbia**
 Product: **Portland Cement Type IL(15) MS**
 Mill Test Report #: **R-TIL-21-08**
 Manufactured: **JULY 2021**

ASTM C595 - 20 Standard Requirements

CHEMICAL ANALYSIS			PHYSICAL ANALYSIS		
Item	Spec limit	Test Result	Item	Spec limit	Test Result
Rapid Method, X-Ray (C 114)			Air content of mortar (%) (C 185)	12 max	5.6
SiO2 (%)	---	18.8	Blaine Fineness (m2/kg) (C 204)	---	473
Al2O3 (%)	---	4.5	Passing 325 (%) (C 430)	---	99.2
Fe2O3 (%)	---	3.0	Autoclave expansion (%) (C 151)	[-0.2 - 0.8]	0.02
CaO (%)	---	63.7	Compressive strength (Mpa [PSI]) (C 109)		
MgO (%)	---	0.8			
SO3 (%)	3.0 max*	2.8			
Loss on ignition @ 950 (%)	10.0 max	5.3			
NaEq (Alkali) (%)	---	0.50			
Insoluble residue (%)	---	0.33			
Adjusted Potential Phase Composition***					
C3S (%)	---	51	3 days	13.0 [1890] min	31.6 4590
C2S (%)	---	15	7 days	20.0 [2900] min	37.5 5430
C3A (%)	---	7	28 days (Reflects previous month's data)	25.0 [3620] min	44.4 6440
C4AF (%)	---	9	Time of setting (minutes)		
			Vicat Initial (C 191)	45-420	86
			Mortar Bar Expansion (C 1038)*		
			14 days, % max	0.020 max	0.002
			Cement Density (C186)		3.09

Sulphate Resistance C1012 (Q2/2021) 0.084

* May exceed 3.0% SO3 maximum based on our C 1038 results of <0.02% expansion at 14 days.

*** Corrected by using ASTM Calculation for Limestone Cement

Cement meets ASTM C 1157 Type MS

We certify that the above described cement, at the time of shipment, meets the chemical and physical requirements of:
 ASTM C 595-20 & AASHTO M 240-20 STANDARD SPECIFICATIONS FOR TYPE IL(15), TYPE IL(15) MS CEMENT

Cement complies with NSF 61

Western BU - Richmond
 7611 No 9 Rd Richmond, BC
 604 244 4300

Questions or enquiries can be directed to Rob Shogren

Rob Shogren, PhD
 Lafarge - Technical Director
 5400 W Marginal Way SW, Seattle WA
 P +1 206 923 9953
 E Rob.Shogren@lafargeholcim.com

Certified By:

Harold Ptachyk B.Sc., PChem
 Quality Manager
 8/9/2021