



MaxCem® Mill Test Report

Month of Issue: August 2021

Plant: Seattle, Washington
 Product: MaxCem® - Type IT(L11)(S30)MS
 Shipped: July 2021
 Mill Test Report Number: SEA_MAXCEM_AUGUST2021

ASTM C 595 and AASHTO M 240 Standard Requirements

CHEMICAL ANALYSIS			PHYSICAL ANALYSIS		
Item	Spec limit	Test Result	Item	Spec limit	Test Result
<i>Rapid Method, X-Ray (C 114)</i>			<i>Air content of mortar (%) (C 185)</i>		
SiO2 (%)	---	24.2		12 max	4
Al2O3 (%)	---	7.9	<i>Blaine Fineness (m2/kg) (C 204)</i>		
Fe2O3 (%)	---	2.5		---	464
CaO (%)	---	57.1	<i>Fineness, Residue retained on a 45 um sieve (%)</i>		
MgO (%)	---	2.4		---	2.2
Sulphate as SO3 (%)	3.0 max*	3.5	<i>Autoclave expansion (%) (C 151)</i>		
Sulfide Sulfur (S) (%)	2.0 max	0.24		0.80 max	-0.03
Loss on ignition (%)	10.0 max	3.4		-0.20 min	
Total Alkalis (Type IL)	---	0.5	<i>Compressive strength (MPa, [PSI]) (C 109)</i>		
Slag addition (%)		30	3 days	13.0 [1890] min	22.0 [3190]
Richmond Type IL (%)		70	7 days	20.0 [2900] min	32.0 [4640]
			28 days, Previous Month	25.0 [3620] min	47.4 [6880]
			<i>Time of setting (minutes)</i>		
			<i>Vicat Initial (C 191)</i>		
				45 - 420	118
			<i>C-1038 Expansion 14-day (%) (C 1038)*</i>		
				0.020	0.000

*Table 1 chemical requirements states that SO3 content above 3.0 is permissible if the C1038 expansion is below 0.020% at 14 days.

We certify that the above described cement, at the time of shipment, meets the chemical and physical ASTM C595 Standard Requirements and AASHTO M 240.

US West BU - Seattle Plant
 5400 W. Marginal Way SW, Seattle, WA 98106
 Phone: 206-937-8025

Certified By:

Daniel Waldron - QC Laboratory Supervisor

August 13, 2021