



65 % recycled materials

TerraFlow® Mill Test Report

Month of Issue: June 2022

Plant: Seattle, Washington

Product: TerraFlow 75
Manufactured: May 2022

Mill Test Report Number: TerraFlow75_June2022

ASTM C 1157 Standard Requirements

CHEMICAL ANALYSIS			PHYSICAL ANALYSIS		
Item	Spec limit	Test Result	Item	Spec limit	Test Result
Slag, % Type IL, %		75 25	Passing 325 Sieve (%)		97.1
			Autoclave expansion (%) Compressive strength (MPa)	0.8	-0.04
			3 days 7 days 28 days	5.0 min 11.0 min 	16.3 25.3 36.1

We certify that the above described cement, at the time of shipment, meets the chemical and physical requirements of applicable Specifications for Type MH

Seattle Plant

5400 W. Marginal Way SW, Seattle, WA 98106

Phone: 206-937-8025

Certified By:

Rob Shogren Technical Director

June 9, 2022

Rolut S. Shoopen