

Mill Test Report Number: SEA\_NEWCEM\_August2022

YEAR: 2022

MONTH OF PRODUCTION: July

PLANT: Seattle

**CEMENT TYPE: NewCem Grade 100** 

Reference Cement				
Fineness by Air Permeability (m²/kg; ASTM C204)	350			
Fineness by 45 µm (No. 325) Sieve (% retain; ASTM C430)	1.9			
Compressive Strength (ASTM C109/C109 M) 7-day 28-day	<b>psi</b> 4,810 5,750	Min Limit - 5,000		
Total Alkalies (Na <sub>2</sub> O + 0.658 K <sub>2</sub> O) (%, ASTM C114)	Actual 0.83	<u>Limits</u> 0.6-0.9		

Slag	
CHEMICAL ANALYSIS	Percent
Silica Dioxide (SiO <sub>2;</sub> ASTM C114)	32.8
Ferric Oxide (Fe <sub>2</sub> O <sub>3</sub> ; ASTM C114)	8.0
Aluminum Oxide (Al <sub>2</sub> O <sub>3</sub> ; ASTM C114)	12.9
Calcium Oxide (CaO; ASTM C114)	41.6
Sulfur Trioxide (SO <sub>3</sub> ; ASTM C114)	4.3
Magnesium Oxide (MgO; ASTM C114)	6.1
Loss on Ignition (L.O.I.; ASTM C114)	0.31
Total Alkalies	0.28
Inorganic Process Addition	3

	Slag		
Fineness by Air Permeability	430		
(m <sup>2</sup> /kg; ASTM C204)			
Fineness by 45 µm (No. 325) Sieve	5.9		
(% retain; ASTM C430)			
Compressive Strength			SAI Limit
(ASTM C109/C109 M)		<u>SAI</u>	<u>Min</u>
28-day (Previous Month)		99	95
Specific Gravity	2.93		
(Mg/m <sup>3</sup> ; ASTM C188)			
	Actual	Max	Limit
Air Content of Mortar	5		12
(%, ASTM C185)			
Sulfide Sulfur	0.8		2.5
(% S, ASTM C114)	0.0	•	2.0
(% 3, A3TW C114)			
Sulfate Ion	3.5		A
(% as SO3, ASTM C114)			
Autoclave expansion	0.000		0.5
(%, CSA A3004-B5)	0.000		
,			
Color Value L*	86.6		

The ground granulated blast furnace slag complies with the current specification of the chemical physical requirement of ASTM C-989, AASHTO M-302 for grade 100 Ground Granulated Blast Furace Slag (GGBFS) and and CSA A3001 Slag.

Slag source is JFE Mineral Company in Kurashiki City, Japan. NewCem is ground and manufactured in Seattle, WA.



Certified by:

Rob Shogren Techincal Director

August 2, 2022

A Not Applicable.