



Cement Test Report

Mill Test Report Number: SEA_NEWCEM_September2022
 YEAR: 2022
 MONTH OF PRODUCTION: August
 PLANT: Seattle
 CEMENT TYPE: NewCem Grade 100

Reference Cement

Fineness by Air Permeability (m ² /kg; ASTM C204)	380		
Fineness by 45 µm (No. 325) Sieve (% retain; ASTM C430)	4.1		
Compressive Strength (ASTM C109/C109 M)		psi	Min Limit
7-day	4,810		-
28-day	5,750		5,000
		Actual	Limits
Total Alkalies (Na₂O + 0.658 K₂O) (%, ASTM C114)	0.84		0.6-0.9

Slag

Fineness by Air Permeability (m ² /kg; ASTM C204)	458		
Fineness by 45 µm (No. 325) Sieve (% retain; ASTM C430)	5.9		
Compressive Strength (ASTM C109/C109 M)		SAI	SAI Limit
28-day (Previous Month)		100	95
Specific Gravity (Mg/m ³ ; ASTM C188)	2.92		
		Actual	Max Limit
Air Content of Mortar (%, ASTM C185)	6		12
Sulfide Sulfur (% S, ASTM C114)	0.8		2.5
Sulfate Ion (% as SO ₃ , ASTM C114)	4.2		A
Autoclave expansion (%, CSA A3004-B5)	-0.005		0.5
Color Value L*	87.0		

Slag


CHEMICAL ANALYSIS	Percent
Silica Dioxide (SiO ₂ ; ASTM C114)	30.4
Ferric Oxide (Fe ₂ O ₃ ; ASTM C114)	0.7
Aluminum Oxide (Al ₂ O ₃ ; ASTM C114)	12.9
Calcium Oxide (CaO; ASTM C114)	41.7
Sulfur Trioxide (SO ₃ ; ASTM C114)	4.99
Magnesium Oxide (MgO; ASTM C114)	5.2
Loss on Ignition (L.O.I.; ASTM C114)	0.82
Total Alkalies	0.34
Inorganic Process Addition	4

^A Not Applicable.

The ground granulated blast furnace slag complies with the current specification of the chemical physical requirement of ASTM C-989, AASHTO M-302 for grade 100 Ground Granulated Blast Furnace Slag (GGBFS) and and CSA A3001 Slag. Slag source is JFE Mineral Company in Kurashiki City, Japan. NewCem is ground and manufactured in Seattle, WA.



Certified by:



Rob Shogren
 Technical Director

September 2, 2022