



# MaxCem® Mill Test Report

Month of Issue: September 2022

Plant: Seattle, Washington  
 Product: MaxCem® - Type IT(L11)(S30)MS  
 Month of Production: August of 2022  
 Mill Test Report Number: SEA\_MAXCEM\_September2022

## ASTM C 595 and AASHTO M 240 Standard Requirements

CHEMICAL ANALYSIS			PHYSICAL ANALYSIS		
Item	Spec limit	Test Result	Item	Spec limit	Test Result
Rapid Method, X-Ray (C 114)			Air content of mortar (%) (C 185)		
SiO2 (%)	---	22.3		12 max	6
Al2O3 (%)	---	7.0	Blaine Fineness (m2/kg) (C 204)		
Fe2O3 (%)	---	2.3		---	494
CaO (%)	---	56.5	Fineness, Residue retained on a 45 um sieve (%)		
MgO (%)	---	2.0		---	3.0
Sulphate as SO3 (%)	3.0 max*	3.4	Autoclave expansion (%) (C 151)		
Loss on ignition (%)	10.0 max	2.8		0.80 max	0.00
Total Alkalis (Type IL)	---	0.34		-0.20 min	
Slag addition (%)		30	Compressive strength ([PSI]) (C 109)		
Richmond Type IL (%)		70		1890 min	3130
				2900 min	4220
				3620 min	6250
			28 days Previous Month		
			Time of setting (minutes)		
			Vicat Initial (C 191)		
				45 - 420	120
			C-1038 Expansion 14-day (%) (C 1038)*		
				0.020	0.005

\*Table 1 chemical requirements states that SO3 content above 3.0 is permissible if the C1038 expansion is below 0.020% at 14 days.

We certify that the above described cement, at the time of shipment, meets the chemical and physical ASTM C595 Standard Requirements and AASHTO M 240.

Lafarge PNW, Inc - Seattle Plant  
 5400 W. Marginal Way SW, Seattle, WA 98106  
 Phone: 206-937-8025

Certified By:

Rob Shogren - Technical Director

September 2, 2022