

Mill Test Report Number: SEA_NEWCEM_November2022 YEAR: 2022 MONTH OF PRODUCTION: October PLANT: Seattle CEMENT TYPE: NewCem Grade 100

Reference Cement			Slag			
Fineness by Air Permeability (m ² /kg; ASTM C204)	410		Fineness by Air Permeability (m²/kg; ASTM C204)	434		
Fineness by 45 μm (No. 325) Sieve (% retain; ASTM C430)	3.6		Fineness by 45 μm (No. 325) Sieve (% retain; ASTM C430)	5.9		
Compressive Strength (ASTM C109/C109 M) 7-day 28-day	psi 4,540 5,390	<u>Min Limit</u> - 5,000	Compressive Strength (ASTM C109/C109 M) 28-day (Previous Month)		SAI 116	SAI Limit <u>Min</u> 95
Total Alkalies (Na ₂ O + 0.658 K ₂ O) (%, ASTM C114)	<u>Actual</u> 0.84	<u>Limits</u> 0.6-0.9	Specific Gravity (Mg/m ³ ; ASTM C188)	2.92		
				Actual	Max	<u>c Limit</u>
Slag CHEMICAL ANALYSIS Silica Dioxide (SiO ₂ : ASTM C114)		Percent 29.5	Air Content of Mortar (%, ASTM C185)	6.4	12	
Ferric Oxide (Fe ₂ O ₃ ; ASTM C114) Aluminum Oxide (Al ₂ O ₃ ; ASTM C114)		0.8 12.9	Sulfide Sulfur (% S, ASTM C114)	0.8	2.5	
Calcium Oxide (CaO; ASTM C114) Sulfur Trioxide (SO ₃ ; ASTM C114) Magnesium Oxide (MgO; ASTM C114) Loss on Ignition (L.O.I.; ASTM C114)		41.7 5 5.1 0.87	Sulfate Ion (% as SO3, ASTM C114)	4.2	A	
Total Alkalies Inorganic Process Addition		0.50 5.4	Autoclave expansion (%, CSA A3004-B5)	-0.010		0.5
			Color Value L*	86.0		

^A Not Applicable.

The ground granulated blast furnace slag complies with the current specification of the chemical physical requirement of ASTM C-989, AASHTO M-302 for grade 100 Ground Granulated Blast Furace Slag (GGBFS) and and CSA A3001 Slag.

Slag source is JFE Mineral Company in Kurashiki City, Japan. NewCem is ground and manufactured in Seattle, WA.



Certified by: ht J. Shoepen

Rob Shogren Techincal Director October 31, 2022