



MaxCem® Mill Test Report

Month of Issue: November 2022

Plant: Seattle, Washington
 Product: MaxCem® - Type IT(L11)(S30)MS
 Month of Production: October of 2022
 Mill Test Report Number: SEA_MAXCEM_November2022

ASTM C 595 and AASHTO M 240 Standard Requirements

CHEMICAL ANALYSIS			PHYSICAL ANALYSIS		
Item	Spec limit	Test Result	Item	Spec limit	Test Result
<i>Rapid Method, X-Ray (C 114)</i>			<i>Air content of mortar (%) (C 185)</i>		
SiO2 (%)	---	24.0		12 max	7
Al2O3 (%)	---	7.6	<i>Blaine Fineness (m2/kg) (C 204)</i>		
Fe2O3 (%)	---	2.5		---	483
CaO (%)	---	59.9	<i>Fineness, Residue retained on a 45 um sieve (%)</i>		
MgO (%)	---	2.3		---	2.7
Sulphate as SO3 (%)	3.0 max*	3.3	<i>Autoclave expansion (%) (C 151)</i>		
Loss on ignition (%)	10.0 max	4.4		0.80 max	0.00
Total Alkalis (Type IL)	---	0.5		-0.20 min	
Slag addition (%)		30	<i>Compressive strength (PSI) (C 109)</i>		
Richmond Type IL (%)		70		1890 min	3050
				2900 min	4250
				3620 min	6400
			<i>Time of setting (minutes)</i>		
				45 - 420	130
			<i>Vicat Initial (C 191)</i>		
				0.020	0.006
			<i>C-1038 Expansion 14-day (%) (C 1038)*</i>		

*Table 1 chemical requirements states that SO3 content above 3.0 is permissible if the C1038 expansion is below 0.020% at 14 days.

We certify that the above described cement, at the time of shipment, meets the chemical and physical ASTM C595 Standard Requirements and AASHTO M 240.

Lafarge PNW, Inc - Seattle Plant
 5400 W. Marginal Way SW, Seattle, WA 98106
 Phone: 206-937-8025

Certified By:

Rob Shogren - Technical Director

October 31, 2022