



## MaxCem® Mill Test Report

Month of Issue: October 2022

Plant: Seattle, Washington

Product: MaxCem® - Type IT(L11)(S30)MS

Month of Production: September of 2022

Mill Test Report Number: SEA\_MAXCEM\_October2022

## ASTM C 595 and AASHTO M 240 Standard Requirements

CHEMICAL ANALYSIS			PHYSICAL ANALYSIS		
Item	Spec limit	Test Result	Item	Spec limit	Test Result
Rapid Method, X-Ray (C 114)					
			Air content of mortar (%) (C 185)	12 max	5
SiO2 (%)		22.8			
			Blaine Fineness (m2/kg) (C 204)		526
Al2O3 (%)		7.3			
			Fineness, Residue retained on a 45 um		3.0
Fe2O3 (%)		2.3	sieve (%)		
CaO (%)		56.6	Autoclave expansion (%) (C 151)	0.80 max	-0.01
. ,				-0.20 min	
MgO (%)		2.3	Compressive strength ([PSI]) (C 109)		
			3 days	1890 min	3120
Sulphate as SO3 (%)	3.0 max*	3.2	7 days	2900 min	4360
			28 days Previous Month	3620 min	6060
Loss on ignition (%)	10.0 max	2.6	Time of setting (minutes)		
(,,,			Vicat Initial (C 191)	45 - 420	114
Total Alkalis (Type IL)		0.49	C-1038 Expansion 14-day (%) (C 1038)*	0.020	0.002
Slag addition (%)		30			
Richmond Type IL (%)		70			

<sup>\*</sup>Table 1 chemical requirements states that SO3 content above 3.0 is permissible if the C1038 expansion is below 0.020% at 14 days.

We certify that the above described cement, at the time of shipment, meets the chemical and physical ASTM C595 Standard Requirements and AASHTO M 240.

Certified By:

Lafarge PNW, Inc - Seattle Plant 5400 W. Marginal Way SW, Seattle, WA 98106

Phone: 206-937-8025

**Rob Shogren - Techincal Director** 

October 3, 2022

Robert D. Shoguen