



Cement Mill Test Report

Date of Issue: January 11, 2023

Plant: Exshaw, AB
 Product: Portland Cement Type I/II/V
 Mill Test Report Number: MTR-I/II/V-2022-12
 Manufactured: December 1-31, 2022

ASTM C 150-21 and AASHTO M 85-18 Standard Requirements

CHEMICAL ANALYSIS			PHYSICAL ANALYSIS		
Item	Spec limit	Test Result	Item	Spec limit	Test Result
Rapid Method, X-Ray (C114)			Air content of mortar (%) (C185)	12 max	5
SiO ₂ (%)	---	20.1	Blaine Fineness (m ² /kg) (C204)	260 min	386
Al ₂ O ₃ (%)	6.0 max	4.0	Passing 45 µm (%) (C430)	---	98.2
Fe ₂ O ₃ (%)	6.0 max	3.6	Autoclave Expansion (%) (C151)*	0.80 max	0.09
CaO (%)	---	62.3	Compressive strength (MPa, [psi]) (C 109)		
MgO (%)	6.0 max	4.7	3 days	12.0 [1740] min	28.7 [4170]
SO ₃ (%)	2.3 max *	2.9	7 days	19.0 [2760] min	36.0 [5210]
Loss on Ignition (%)	3.5 max	2.5	28 days (Reflects previous month's data)		44.5 [6450]
Insoluble Residue (%)*	1.5 max	0.65	Time of setting (minutes)		
CO ₂ (%)	---	1.8	Vicat Initial (C191)	45 - 375	121
Limestone (%)	5.0 max	4.4	Sulfate Resistance (%) (C452)*	0.040 max	0.030
CaCO ₃ in Limestone (%)	70 min	90.9	Mortar Bar Expansion (%) (C1038)	0.020 max	0.010
Inorganic Process Addition (Lafarge Cement Kiln Dust)	5.0 max	-			
Adjusted Potential Phase Composition (C 50)					
C ₃ S (%)	---	53			
C ₂ S (%)	---	18			
C ₃ A (%)	5 max	4			
C ₄ AF (%)	---	11			
C ₄ AF + 2(C ₃ A)	25 max	19			
C ₃ S+4.75*C ₃ A (%)	100 max	73			
ASTM C 150-17 and AASHTO M 85-17 Optional Requirements:					
NaEq (%)	0.60 max	0.57	False set (%) (C451)	50 min	67

* May exceed the SO₃ maximum based on C 1038 results of <0.020% expansion at 14 days.

** Current Production run not available - most recent provided

We certify that the above described cement, at the time of shipment, meets the chemical and physical requirements of ASTM C 150-21 & AASHTO M 85-18 STANDARD SPECIFICATIONS FOR TYPES I, II & V CEMENTS; and ASTM C 150-21 & AASHTO M 85-18 OPTIONAL CHEMICAL REQUIREMENTS FOR TYPES I, II & V LOW ALKALI CEMENT.

Certified By:

Lorraine Johnson

Western Canada BU - Exshaw Plant
 P.O. Box 160, Highway 1A, Exshaw AB, T0L 2C0
 Phone: 403-673-3815

Lorraine Johnson
 Quality Manager



Cement Mill Test Report

Date of Issue: January 11, 2023

Plant: Exshaw AB
Product: Portland Cement Type I/II/V
Mill Test Report Number: MTR-I/II/V-2022-12
Manufactured: December 1-31, 2022

ASTM C 150-21 and AASHTO M 85-18 Standard Requirements

Additional Data

Item	Test Result	
	Limestone	Inorganic Process Addition Lafarge Cement Kiln Dust
Amount (%)	4.4	-
SiO ₂ (%)	1.8	n/a
Al ₂ O ₃ (%)	0.7	n/a
Fe ₂ O ₃ (%)	0.2	n/a
CaO (%)	50.9	n/a
SO ₃ (%)	0.2	n/a
CO ₂ (%)	42.0	n/a

Base Cement Phase Composition

Item	Test Result
C ₃ S (%)	55
C ₂ S (%)	18
C ₃ A (%)	5
C ₄ AF (%)	11

We certify that the data above reflects the materials used in cement manufacture during the production period indicated.

Note: Specific Gravity for Portland Cements is 3.14

Western Canada BU - Exshaw Plant
P.O. Box 160, Highway 1A, Exshaw AB, T0L 2C0
Phone: 403-673-3815

Certified By:

Lorraine Johnson

Lorraine Johnson
Quality Manager