



**Cement**

**FLY ASH TEST REPORT**

Analysis by: Lafarge Seattle Concrete Lab  
Sample from : Centralia Power Plant  
Average Analysis: April 2023  
Test Report Number 5-23 Class F

**Chemical Analysis**

	<b>Results</b>	<b>Limits</b>
Silicon Dioxide (SiO <sub>2</sub> )	<b>46.0 %</b>	
Aluminum Oxide (Al <sub>2</sub> O <sub>3</sub> )	<b>18.2 %</b>	
Iron Oxide (Fe <sub>2</sub> O <sub>3</sub> )	<b>5.7 %</b>	
Total (SiO <sub>2</sub> ) + (Al <sub>2</sub> O <sub>3</sub> ) + (Fe <sub>2</sub> O <sub>3</sub> )	<b>70 %</b>	50% Min - ASTM
Sulphur Trioxide (SO <sub>3</sub> )	<b>1.4 %</b>	5% Max - ASTM
Calcium Oxide (CaO)	<b>17.1 %</b>	18% Max - ASTM
Magnesium Oxide	<b>4.5 %</b>	
Moisture Content	<b>0.15 %</b>	3% Max - ASTM
Loss on Ignition	<b>0.42 %</b>	5% Max
Available Alkali as Equiv. Na <sub>2</sub> O ( <i>previous month's result</i> )	<b>0.75 %</b>	1.5% Max

**Physical Analysis**

Fineness Retained on 45 um (No. 325 Sieve)	<b>15.4 %</b>	34% Max - ASTM
Strength Activity Index with Portland Cement		
% of Control at 7 Days	<b>104 %</b>	75% Min - ASTM
% of Control at 28 Days ( <i>previous month's result</i> )	<b>109 %</b>	75% Min - ASTM
Water Requirement, Percent of Control	<b>95 %</b>	105% Max- ASTM
Autoclave Expansion	<b>0.03 %</b>	0.8% Max - ASTM
Density	<b>2.66 Mg/m<sup>3</sup></b>	

**Uniformity Requirements**

Density, Variation from Average	<b>0.00 %</b>	5% Max - ASTM
Fineness 45um Sieve, Variation from Average	<b>0.60 %</b>	5% Max - ASTM

We hereby certify that the composite fly ash sample above meets the chemical and physical requirements of ASTM C618 and AASHTO M295 for class F fly ash.

Certified : \_\_\_\_\_

Rob Shogren  
Technical Director

**WESTERN REGION**

5400 West Marginal Way SW, Seattle, Washington 98106-1517  
Office: 206.923.0098 or 800.477.0100 Fax: 206.923.0388