

Cement Mill Test Report

Month of Issue: January 2024

Plant: **Richmond, British Columbia**
 Product: **Portland Cement Type GUL / MSL**
 Mill Test Report #: **R-GUL-24-01**
 Manufactured: **December 2023**

CSA A3001- 18 Standard Requirements

CHEMICAL ANALYSIS			PHYSICAL ANALYSIS		
Item	Spec limit	Test Result	Item	Spec limit	Test Result
Rapid Method, X-Ray			Air content of mortar (%) (C 185)	---	5.2
SiO ₂ (%)	---	18.8	Blaine Fineness (m ² /kg)	---	464
Al ₂ O ₃ (%)	---	4.5	Passing 45 um (%)	72 min	99.4
Fe ₂ O ₃ (%)	---	3.1	Compressive strength (MPa)		
CaO (%)	---	62.4	3 days	14.5 min	30.2
MgO (%)	---	0.9	7 days	20.0 min	37.4
SO ₃ (%)	3.0 max*	2.7	28 days (Reflects previous month's data)	26.5 min	45.7
Loss on ignition @ 950 (%)	10.0 max	6.4	Time of setting (minutes)		
Insoluble residue (%)	---	0.50	Vicat Initial	45-375	103
Free Lime (%)	---	0.9	Sulphate Resistance (C8)	0.10	0.092
Inorganic Process Addition (%)		3.5	Sulphate Resistance (C6)	---	0.03
Limestone Content (%)		12.9	Colour (L*)	---	64
Potential Phase Composition**			Cement Density		3.09
C3S (%)	---	69			
C2S (%)	---	24			
C3A (%)	---	7			
C4AF (%)	---	9			

CSA A3001-18 Optional Chemical Requirements:

NaEq (Alkali) (%) 0.46

* May exceed 3.0% SO₃ maximum based on our A3004-C5 results of <0.020% expansion at 14 days.

**Corrected by using ASTM Calculation for Limestone Cement


We certify that the above described cement, at the time of shipment, meets the chemical and physical requirements of applicable specifications for Type GUL / MSL
 CSA A3001-18 STANDARD SPECIFICATIONS FOR TYPE GUL / MSL CEMENT;
 Cement complies with NSF 61

Western BU - Richmond
 7611 No 9 Rd Richmond, BC
 604 244 4300

Questions or enquiries can be directed to Paul Deram

Paul Deram
 Lafarge - Technical Services Engineer
 7591 #9 Road, Richmond, BC, V6W 0A6 Canada
 C +1 604 328 7793
 E paul.deram@lafarge.com

Certified By:



Robyn van Zutphen
 Quality Manager
 1/8/2024