



Cement Mill Test Report

Date of Issue: February 13, 2025

Plant: Exshaw, AB
Product: Portland Cement Type III
Mill Test Report Number: ESW_Type III 2025-01
Manufactured during the month of: January 2025

ASTM C 150-24 and AASHTO M 85-24 Standard Requirements

CHEMICAL ANALYSIS			PHYSICAL ANALYSIS		
Item	Spec limit	Test Result	Item	Spec limit	Test Result
Rapid Method, X-Ray (XRF) (C114)			Air content of mortar (%) (C185)		
SiO ₂ (%)	---	19.0		12 max	6
Al ₂ O ₃ (%)	---	4.0	Blaine Fineness (m ² /kg) (C204)		
Fe ₂ O ₃ (%)	---	3.3		---	489
CaO (%)	---	61.7	Passing 45 µm (%) (C430)		
MgO (%)	6.0 max	4.6		---	99.1
SO ₃ (%) **	3.5 max	3.4	Compressive strength (MPa, [psi]) (C109)		
Loss on Ignition (%)	3.5 max	2.6	1 day	12.0 [1740] min	22.0 [3194]
Insoluble Residue (%)	1.5 max	0.3	3 days	24.0 [3480] min	33.5 [4864]
CO ₂ (%)	---	1.9	28 days (Previous Month's Result)		48.3 [7010]
Limestone (%)	5.0 max	4.4	Time of setting (minutes)		
CaCO ₃ in Limestone (%)	70 min	96.0	Vicat Initial (C191)	45 - 375	83
Inorganic Process Addition (Lafarge Cement Kiln Dust)	5.0 max	--	Mortar Bar Expansion (%) (C1038)		
Adjusted Potential Phase Composition (C150)				0.020 max	0.012
C ₃ S (%)	---	57			
C ₂ S (%)	---	11			
C ₃ A (%)	15 max	5			
C ₄ AF (%)	---	10			

ASTM C 150-24 and AASHTO M 85-24 Optional Chemical Requirements:

Na₂Oeq (%) Weekly Averages: Week 1 0.60 Week 2 0.56 Week 3 0.56 Week 4 0.57 Max 0.60

** May exceed 3.0% SO₃ maximum based on C1038 results of <0.020% expansion at 14 days.

We certify that the above described cement, at the time of shipment, meets the chemical and physical requirements of:

ASTM C 150-24 & AASHTO M 85-24 STANDARD SPECIFICATIONS FOR TYPE III CEMENT; and
ASTM C 150-24 & AASHTO M 85-24 OPTIONAL CHEMICAL REQUIREMENTS FOR TYPE III LOW ALKALI CEMENT.

Exceptions: C430 is excluded from the scope of the AASHTO accreditation.

Western Canada BU - Exshaw Plant
P.O. Box 160, Highway 1A, Exshaw AB, T0L 2C0
Phone: 403-673-3815

Certified By:


John W Blair
Quality Manager





Cement Mill Test Report

Date of Issue: February 13, 2025

Plant: Exshaw, AB
Product: Portland Cement Type III
Mill Test Report Number: ESW_Type III 2025-01
Manufactured: January 2025

ASTM C 150-24 and AASHTO M 85-24 Standard Requirements

Additional Data

Item	Test Result	
	Limestone	Inorganic Process Addition Lafarge Cement Kiln Dust
Amount (%)	4.4	--
SiO ₂ (%)	2.1	13.6
Al ₂ O ₃ (%)	0.5	3.4
Fe ₂ O ₃ (%)	0.2	2.0
CaO (%)	49.0	50.2
SO ₃ (%)	0.3	4.7
CO ₂ (%)	42.3	n/a

Base Cement Phase Composition

Item	Test Result
C ₃ S (%)	60
C ₂ S (%)	12
C ₃ A (%)	5
C ₄ AF (%)	10

Specific Gravity (For Information Purposes Only) 3.15

We certify that the data above reflects the materials used in cement manufacture during the production period indicated.

Western Canada BU - Exshaw Plant
P.O. Box 160, Highway 1A, Exshaw AB, T0L 2C0
Phone: 403-673-3815

Certified By:


John W Blair
Quality Manager