



MaxCem® Mill Test Report

Month of Issue: April 2025

Plant: Seattle, Washington
Product: MaxCem® - Type IT(L11)(S30)MS
Month of Production: March 2025
Mill Test Report Number: SEA_MAXCEM_April_2025

ASTM C 595 and AASHTO M 240 Standard Requirements

CHEMICAL ANALYSIS			PHYSICAL ANALYSIS		
Item	Spec limit	Test Result	Item	Spec limit	Test Result
Rapid Method, X-Ray (C 114)					
SiO ₂ (%)	---	22.5	Air content of mortar (%) (C 185)	12 max	7
Al ₂ O ₃ (%)	---	6.7	Blaine Fineness (m ² /kg) (C 204)	---	499
Fe ₂ O ₃ (%)	---	2.4	Fineness, Residue retained on a 45 um sieve (%)	---	1.5
CaO (%)	---	55.2	Compressive strength ([PSI]) (C 109)		
MgO (%)	---	2.7			
Sulphate as SO ₃ (%)	3.0 max*	3.1			
Loss on ignition (%)	10.0 max	5.1			
Total Alkalis (Type IL)	---	0.53	3 days	1890 min	2930
Slag addition (%)		30	7 days	2900 min	4210
Richmond Type IL (%)		70	28 days Previous Month	3620 min	5540
			Time of setting (minutes)	45 - 420	156
			Vicat Initial (C 191)		
			C-1038 Expansion 14-day (%) (C 1038)*	0.020	0.001

*Table 1 chemical requirements states that SO₃ content above 3.0 is permissible if the C1038 expansion is below 0.020% at 14 days.

We certify that the above described cement, at the time of shipment, meets the chemical and physical ASTM C595 Standard Requirements and AASHTO M 240.

Lafarge PNW, Inc - Seattle Plant
5400 W. Marginal Way SW, Seattle, WA 98106
Phone: 206-937-8025

Certified By:

Rob Shogren - Technical Director

April 2, 2025