

Cement Mill Test Report

Date of Issue: May 08, 2025

Plant: Exshaw AB

Product: Portland Cement Type I/II
Mill Test Report Number: ESW_Type I-II 2025-04

Manufactured during the month of: April 2025

ASTM C 150-24 and AASHTO M 85-24 Standard Requirements

CHEMICAL ANALYSIS PHYSICAL ANALYSIS Test Result Spec limit Spec limit Test Result Rapid Method, X-Ray (C114) Air content of mortar (%) (C185) 12 max SiO₂ (%) 19.3 Blaine Fineness (m²/kg) (C204) Al₂O₃ (%) 6.0 max 4.0 260 min 383 Fe₂O₃ (%) 6.0 max 3.5 CaO (%) 61.7 Passing 45 µm (%) (C430) 98.5 MgO (%) 6.0 max 4.8 Compressive strength (MPa, [psi]) (C 109) SO₃ (%)* 3.0 max * 3.3 Loss on Ignition (%) 3.5 max 24 Insoluble Residue (%) 12.0 [1740] min 27.8 [4035] 1.5 max 0.3 3 days 19.0 [2760] min 1.8 33.2 [4813] CO₂ (%) 7 days 5.0 max 28 days (Previous Month's Result) 42.5 [6163] Limestone (%) 4.2 CaCO₃ in Limestone (%) 70 min 96.0 **Inorganic Process Addition** 5.0 max Time of setting (minutes) (Lafarge Cement Kiln Dust) Vicat Initial (C191) 45 - 375 90 Adjusted Potential Phase Composition (C50) Mortar Bar Expansion (%) (C1038)** 0.020 max 0.016 C₃S (%) C2S (%) 13 C₃A (%) 5 8 max C₄AF (%) 10 C₃S+4.75*C₃A (%) 100 max 79

ASTM C 150-17 and AASHTO M 85-17 Optional Requirements:

Na2Oeq 0.60 max 0.55 False set (%) (C451) 50 min 74

We certify that the above described cement, at the time of shipment, meets the chemical and physical requirements of:

ASTM C 150-24 & AASHTO M 85-24 STANDARD SPECIFICATIONS FOR TYPES I / II CEMENTS; and

ASTM C 150-24 & AASHTO M 85-24 OPTIONAL CHEMICAL REQUIREMENTS FOR TYPES I / II LOW ALKALI CEMENT.

AASHTO Accrediation Exceptions: C430

Western Canada BU - Exshaw Plant P.O. Box 160, Highway 1A, Exshaw AB, T0L 2C0

Phone: 403-673-3815

Certified By:

John W Blair Quality Manager

 $^{^{\}star}$ May exceed the SO $_{\!3}$ maximum $\,$ based on C 1038 results of <0.020% expansion at 14 days.



Cement Mill Test Report

Date of Issue: May 08, 2025

Plant: Exshaw AB

Product: Portland Cement Type I/II
Mill Test Report Number: ESW_Type I-II 2025-04

Manufactured: April 2025

ASTM C 150-24 and AASHTO M 85-24 Standard Requirements

Additional Data

Item	Test Result	
	Limestone	Inorganic Process Addition
		Lafarge Cement Kiln Dust
Amount (%)	4.2	
SiO ₂ (%)	2.8	13.8
Al ₂ O ₃ (%)	0.5	3.7
Fe ₂ O ₃ (%)	0.4	2.0
CaO (%)	47.8	45.7
SO ₃ (%)	0.2	2.9
CO ₂ (%)	42.4	n/a

Base Cement Phase Composition

Item	Test Result
C ₃ S (%)	58
C ₂ S (%)	14
C ₃ A (%)	5
C ₄ AF (%)	11

Specific Gravity: 3.16 For information purposes only.

We certify that the data above reflects the materials used in cement manufacture during the production period indicated.

Western Canada BU - Exshaw Plant P.O. Box 160, Highway 1A, Exshaw AB, T0L 2C0

Phone: 403-673-3815

Certified By:

Quality Manager