

Cement Mill Test Report

Date of Issue: June 05, 2025

Plant: Product: Mill Test Report Number: Manufactured during the month of: Exshaw AB Portland Cement Type I/II ESW_Type I-II 2025-05 May 2025

ASTM C 150-24 and AASHTO M 85-24 Standard Requirements

CHEMICAL ANALYSIS			PHYSICAL ANALYSIS		
Item	Spec limit	Test Result	ltem	Spec limit	Test Result
Rapid Method, X-Ray (C114)			Air content of mortar (%) (C185)	12 max	5
SiO ₂ (%)		19.1			
Al ₂ O ₃ (%)	6.0 max	4.0	Blaine Fineness (m ² /kg) (C204)	260 min	405
Fe ₂ O ₃ (%)	6.0 max	3.5			
CaO (%)		61.6	Passing 45 μm (%) (C430)		98.5
MgO (%)	6.0 max	4.8			
SO ₃ (%)*	3.0 max *	3.3	Compressive strength (MPa, [psi]) (C 10	9)	
Loss on Ignition (%)	3.5 max	2.7			
Insoluble Residue (%)	1.5 max	0.3	3 days	12.0 [1740] min	27.3 [3963]
CO ₂ (%)		1.9	7 days	19.0 [2760] min	32.7 [4746]
Limestone (%)	5.0 max	4.4	28 days (Previous Month's Result)		41.9 [6081]
CaCO₃ in Limestone (%)	70 min	97.0			
Inorganic Process Addition	5.0 max	0.3	Time of setting (minutes)		
(Lafarge Cement Kiln Dust)			Vicat Initial <i>(C191)</i>	45 - 375	87
Adjusted Potential Phase Co	mposition (C50)		Mortar Bar Expansion (%) (C1038)**	0.020 max	0.016
C ₃ S (%)		57			
C ₂ S (%)		11			
C₃A (%)	8 max	5			
C₄AF (%)		11			
C ₃ S+4.75*C ₃ A (%)	100 max	81			
ARTM C 450 47 and AARUTA	M OF 47 Onting		1		
ASTM C 150-17 and AASHTC Na2Oeq	0.60 max	0.55	False set (%) <i>(C</i>	451) 50 min	78

	C 1038 results of <0.020% expansion at 14 days.		NSE
We certify that the above describ	bed cement, at the time of shipment, meets t	he chemical and	
physical requirements of:			
ASTM C 150-24 & AASHTO M 85-	24 STANDARD SPECIFICATIONS FOR TYPE	S I / II CEMENTS; and	
ASTM C 150-24 & AASHTO M 85-	24 OPTIONAL CHEMICAL REQUIREMENTS I	FOR TYPES I / II LOW ALKALI CE	EMENT.
AASHTO Accrediation Exceptions: C43	0	, ~	
			$\sum \alpha \alpha$
Western Canada BU - Exshaw	/ Plant C	certified By:	JAN .
P.O. Box 160, Highway 1A, Exshaw AB,		-24-~	K K
Phone: 403-673-3815	—	🖉 John W Blair	
		Quality Manage	er
		/	-



Cement Mill Test Report

Date of Issue: June 05, 2025

Plant: Product: Mill Test Report Number: Manufactured: Exshaw AB Portland Cement Type I/II ESW_Type I-II 2025-05 May 2025

ASTM C 150-24 and AASHTO M 85-24 Standard Requirements

Additional Data

Item	Test Result		
	Limestone	Inorganic Process Addition	
		Lafarge Cement Kiln Dust	
Amount (%)	4.4		
SiO ₂ (%)	2.1	14.2	
Al ₂ O ₃ (%)	0.5	3.6	
Fe ₂ O ₃ (%)	0.4	2.1	
CaO (%)	48.9	48.7	
SO ₃ (%)	0.2	2.2	
CO ₂ (%)	42.5	n/a	

Base Cement Phase Composition

Item	Test Result
C ₃ S (%)	60
C ₂ S (%)	12
C ₃ A (%)	5
C₄AF (%)	11

Specific Gravity:

3.16 For information purposes only.

We certify that the data above reflects the materials used in cement manufacture during the production period indicated.

Western Canada BU - Exshaw Plant P.O. Box 160, Highway 1A, Exshaw AB, TOL 2C0 Phone: 403-673-3815

Certified By: John W Blair Quality Manager