

Cement Mill Test Report

Date of Issue: October 7, 2025

Plant: Exshaw, AB

Product: Portland Cement Type III Mill Test Report Number: ESW_Type III 2025-09 Manufactured during the month of: September 2025

ASTM C 150-24 and AASHTO M 85-24 Standard Requirements

CHEMICAL ANALYSIS PHYSICAL ANALYSIS Spec limit **Test Result** ltem Spec limit Test Result ltem Rapid Method, X-Ray (XRF) (C114) Air content of mortar (%) (C185) 12 max 6 SiO₂ (%) 19.0 Blaine Fineness (m²/kg) (C204) Al₂O₃ (%) 3.9 469 Fe₂O₃ (%) 3.5 CaO (%) 61.4 Passing 45 μm (%) (C430) 99.2 MgO (%) 6.0 max 4.6 Compressive strength (MPa, [psi]) (C109) SO₃ (%) ** 3.5 max 3.4 12.0 [1740] min Loss on Ignition (%) 3.5 max 2.5 1 day 20.9 [3032] Insoluble Residue (%) 0.5 3 days 24.0 [3480] min 32.1 [4650] 1.5 max 28 days (Previous Month's Result) CO2 (%) 1.8 43.3 [6273] Limestone (%) 5.0 max 4.1 70 min CaCO₃ in Limestone (%) 96.0 Inorganic Process Addition 5.0 max 0.5 Time of setting (minutes) (Lafarge Cement Kiln Dust) Vicat Initial (C191) 45 - 375 87 Adjusted Potential Phase Composition (C150) Mortar Bar Expansion (%) (C1038) 0.020 max 0.014 C₃S (%) 57 C2S (%) 12 C₃A (%) 15 max 4 C₄AF (%) 11

ASTM C 150-24 and AASHTO M 85-24 Optional Chemical Requirements:

Na₂Oeq (%) Weekly Averages: Week 1 0.55 Week 2 0.56 Week 4 0.58 Max 0.60 Week 3 0.57

** May exceed 3.0% SO3 maximum based on C1038 results of <0.020% expansion at 14 days.

We certify that the above described cement, at the time of shipment, meets the chemical and physical requirements of:

ASTM C 150-24 & AASHTO M 85-24 STANDARD SPECIFICATIONS FOR TYPE III CEMENT; and

ASTM C 150-24 & AASHTO M 85-24 OPTIONAL CHEMICAL REQUIREMENTS FOR TYPE III LOW ALKALI CEMENT.

Exceptions: C430 is excluded from the scope of the AASHTO accreditation.

Western Canada BU - Exshaw Plant P.O. Box 160, Highway 1A, Exshaw AB, T0L 2C0

Phone: 403-673-3815

AASHIO

Certified By:

John W Blair **Quality Manager**



Cement Mill Test Report

Date of Issue: October 7, 2025

Plant: Exshaw, AB

Product: Portland Cement Type III
Mill Test Report Number: ESW_Type III 2025-09

Manufactured: September 2025

ASTM C 150-24 and AASHTO M 85-24 Standard Requirements

Additional Data

Item	Test Result	
	Limestone	Inorganic Process Addition
		Lafarge Cement Kiln Dust
Amount (%)	4.1	
SiO ₂ (%)	1.7	14.8
Al_2O_3 (%)	0.5	3.6
Fe ₂ O ₃ (%)	0.2	2.4
CaO (%)	49.8	51.0
SO ₃ (%)	0.2	2.2
CO ₂ (%)	42.2	n/a

Base Cement Phase Composition

Item	Test Result
C ₃ S (%)	59
C ₂ S (%)	12
C ₃ A (%)	5
C ₄ AF (%)	11

Specific Gravity (For Information Purposes Only) 3.15

We certify that the data above reflects the materials used in cement manufacture during the production period indicated.

Certified By:

John W Blair Quality Manager

Western Canada BU - Exshaw Plant P.O. Box 160, Highway 1A, Exshaw AB, T0L 2C0

Phone: 403-673-3815