



Cement Mill Test Report

Date of Issue: November 17, 2025

Plant: Exshaw, AB
Product: Portland Cement Type III
Mill Test Report Number: ESW_Type III 2025-10
Manufactured during the month of: October 2025

ASTM C 150-24 and AASHTO M 85-24 Standard Requirements

CHEMICAL ANALYSIS			PHYSICAL ANALYSIS		
Item	Spec limit	Test Result	Item	Spec limit	Test Result
Rapid Method, X-Ray (XRF) (C114)			Air content of mortar (%) (C185)		
SiO ₂ (%)	---	19.0		12 max	6
Al ₂ O ₃ (%)	---	4.1	Blaine Fineness (m ² /kg) (C204)		
Fe ₂ O ₃ (%)	---	3.5		---	508
CaO (%)	---	61.5	Passing 45 µm (%) (C430)		
MgO (%)	6.0 max	4.7		---	99.2
SO ₃ (%) **	3.5 max	3.5	Compressive strength (MPa, [psi]) (C109)		
Loss on Ignition (%)	3.5 max	2.4	1 day	12.0 [1740] min	24.5 [3555]
Insoluble Residue (%)	1.5 max	0.5	3 days	24.0 [3480] min	35.0 [5075]
CO ₂ (%)	---	1.7	28 days (Previous Month's Result)		45.0 [6526]
Limestone (%)	5.0 max	4.0	Time of setting (minutes)		
CaCO ₃ in Limestone (%)	70 min	97.0	Vicat Initial (C191)	45 - 375	71
Inorganic Process Addition (Lafarge Cement Kiln Dust)	5.0 max	0.5	Mortar Bar Expansion (%) (C1038)		
Adjusted Potential Phase Composition (C150)				0.020 max	0.011
C ₃ S (%)	---	56			
C ₂ S (%)	---	12			
C ₃ A (%)	15 max	5			
C ₄ AF (%)	---	11			

ASTM C 150-24 and AASHTO M 85-24 Optional Chemical Requirements:

Na₂Oeq (%) Weekly Averages: Week 1 0.57 Week 2 0.59 Week 3 0.59 Week 4 0.57 Max 0.60

** May exceed 3.0% SO₃ maximum based on C1038 results of <0.020% expansion at 14 days.

We certify that the above described cement, at the time of shipment, meets the chemical and physical requirements of:

ASTM C 150-24 & AASHTO M 85-24 STANDARD SPECIFICATIONS FOR TYPE III CEMENT; and
ASTM C 150-24 & AASHTO M 85-24 OPTIONAL CHEMICAL REQUIREMENTS FOR TYPE III LOW ALKALI CEMENT.

Exceptions: C430 and C191 are excluded from the scope of the AASHTO accreditation.

Western Canada BU - Exshaw Plant
P.O. Box 160, Highway 1A, Exshaw AB, T0L 2C0
Phone: 403-673-3815

Certified By:


John W Blair
Quality Manager





Cement Mill Test Report

Date of Issue: November 17, 2025

Plant: Exshaw, AB
Product: Portland Cement Type III
Mill Test Report Number: ESW_Type III 2025-10
Manufactured: October 2025

ASTM C 150-24 and AASHTO M 85-24 Standard Requirements

Additional Data

Item	Test Result	
	Limestone	Inorganic Process Addition Lafarge Cement Kiln Dust
Amount (%)	4.0	--
SiO ₂ (%)	1.7	14.8
Al ₂ O ₃ (%)	0.4	3.6
Fe ₂ O ₃ (%)	0.2	2.4
CaO (%)	49.5	51.0
SO ₃ (%)	0.1	2.2
CO ₂ (%)	42.6	n/a

Base Cement Phase Composition

Item	Test Result
C ₃ S (%)	59
C ₂ S (%)	12
C ₃ A (%)	5
C ₄ AF (%)	11

Specific Gravity (For Information Purposes Only) 3.15

We certify that the data above reflects the materials used in cement manufacture during the production period indicated.

Western Canada BU - Exshaw Plant
P.O. Box 160, Highway 1A, Exshaw AB, T0L 2C0
Phone: 403-673-3815

Certified By:


John W Blair
Quality Manager