



FLY ASH TEST REPORT

Analysis by: Amrize Seattle Concrete Lab
Sample from : Centralia Power Plant
Average Analysis: November 2025
Test Report Number 12-25 Class F

Chemical Analysis

	Results	Limits
Silicon Dioxide (SiO_2)	47.9 %	
Aluminum Oxide (Al_2O_3)	17.9 %	
Iron Oxide (Fe_2O_3)	6.0 %	
Total (SiO_2) + (Al_2O_3) + (Fe_2O_3)	72 %	50% Min - ASTM
Sulphur Trioxide (SO_3)	1.1 %	5% Max - ASTM
Calcium Oxide (CaO)	15.3 %	18% Max - ASTM
Magnesium Oxide	4.3 %	
Moisture Content	0.22 %	3% Max - ASTM
Loss on Ignition	0.37 %	5% Max
Available Alkali as Equiv. Na_2O (previous month's result)	0.62 %	1.5% Max


Physical Analysis

Fineness Retained on 45 um (No. 325 Sieve)	12.2 %	34% Max - ASTM
Strength Activity Index with Portland Cement		
% of Control at 7 Days	94 %	75% Min - ASTM
% of Control at 28 Days (previous month's result)	102 %	75% Min - ASTM
Water Requirement, Percent of Control	93 %	105% Max- ASTM
Density	2.65 Mg/m^3	

Uniformity Requirements

Density, Variation from Average	0.20 %	5% Max - ASTM
Fineness 45um Sieve, Variation from Average	1.90 %	5% Max - ASTM

We hereby certify that the composite fly ash sample above meets the chemical and physical requirements of ASTM C618 and AASHTO M295 for class F fly ash.

Certified : 

Rob Shogren
Technical Director

WESTERN REGION

5400 West Marginal Way SW, Seattle, Washington 98106-1517

Office: 206.923.0098 or 800.477.0100 Fax: 206.923.0388