



FLY ASH TEST REPORT

Sample from : Sundance Harvested Fly Ash
Average Analysis: January 2026
Test Report Number Sundance_HA-2-26_F_CSA

Chemical Analysis

Silicon Dioxide (SiO ₂)	60.0 %
Aluminum Oxide (Al ₂ O ₃)	23.1 %
Iron Oxide (Fe ₂ O ₃)	3.7 %
Total (SiO ₂) + (Al ₂ O ₃) + (Fe ₂ O ₃)	86.8 %
Sulphur Trioxide (SO ₃)	0.4 %
Calcium Oxide (CaO)	8.4 %
Magnesium Oxide	0.8 %
Moisture Content	0.04 %
Loss on Ignition	2.32 %
Total Alkalies as Equivalent Na ₂ O	2.37 %

Physical Analysis

Fineness Retained on 45 um (No. 325 Sieve)	16.4 %
Fineness Retained on 160 um	0.7
Quality of Air Entrianment	1.0 %
Strength Activity Index with Portland Cement	
% of Control at 28 Days (<i>previous month's result</i>)	93 %
Water Requirement, Percent of Control	100 %
Density	2.32 g/cm ³
Density, Variation from Average	1.20 %
Fineness 45um Sieve, Variation from Average	3.10 %

We hereby certify that the composite fly ash sample above meets the chemical, physical and testing frequency requirements of CAN/CSA A3001 for Type F Fly Ash.

* Tested at CCIL, ASTM C1077 and AASHTO R18 Accredited Laboratory

Rob Shogren, P.Eng, Ph.D.
Technical Director
Amrize