



MaxCem® Mill Test Report

Month of Issue: June 2026

Plant: Seattle, Washington
Product: MaxCem® - Type IT(L11)(S30)MS & GULb-30S
Month of Production: May 2026
Mill Test Report Number: SEA_MAXCEM_June_2026

ASTM C 595, AASHTO M 240 and CSA A3000 Standard Requirements

CHEMICAL ANALYSIS			PHYSICAL ANALYSIS		
Item	Spec limit	Test Result	Item	Spec limit	Test Result
Rapid Method, X-Ray (C 114)					
SiO ₂ (%)	---	21.6	Air content of mortar (%) (C 185)	12 max	7
Al ₂ O ₃ (%)	---	7.0	Blaine Fineness (m ² /kg) (C 204)	---	445
Fe ₂ O ₃ (%)	---	2.6	Fineness, Residue retained on a 45 um sieve (%)	---	1.9
CaO (%)	---	55.9	Compressive strength PSI [MPa] (C 109)	1890 min 2900 min 3620 min	2680 [18.5] 4050 [27.9] 6500 [44.8]
MgO (%)	---	2.3			
Sulphate as SO ₃ (%)	3.0 max*	3.2			
Loss on ignition (%)	10.0 max	5.5			
Total Alkalis (Type IL)	---	0.49	Time of setting (minutes) Vicat Initial (C 191)	45 - 420	145
Slag addition (%)		30	C-1038 Expansion 14-day (%) (C 1038)*	0.020	-0.003
Richmond Type IL (%)		70			

*Chemical requirements states that SO₃ content above 3.0 is permissible if the C1038 expansion is below 0.020% at 14 days.

We certify that the above described cement, at the time of shipment, meets the chemical and physical ASTM C595, AASHTO M 240 and CSA A3000 Standard Requirements

Amrize - Seattle Plant
5400 W. Marginal Way SW, Seattle, WA 98106
Phone: 206-937-8025

Certified By:

Rob Shogren - Technical Director

June 2, 2026