



Mill Test Report

Month of Issue: July 2026

Plant: Seattle, Washington
Product: TerraFlow 90
Manufactured: June 2026
Mill Test Report Number: TerraFlow90_July_2026

ASTM C 1157 Standard Requirements

CHEMICAL ANALYSIS			PHYSICAL ANALYSIS		
Item	Spec limit	Test Result	Item	Spec limit	Test Result
Slag, %	---	90	Passing 325 Sieve (%)	---	96.4
Type IL, %	---	10	Blaine Fineness (m2/kg) (C 204)	---	464
			Compressive strength (MPa)		
			3 days	5.0 min	11.9
			7 days	11.0 min	17.7
			28 days	--	24.3

We certify that the above described cement, at the time of shipment, meets the chemical and physical requirements of applicable Specifications for Type MH

Seattle Plant
5400 W. Marginal Way SW, Seattle, WA 98106
Phone: 206-937-8025

Certified By:

Rob Shogren - Technical Director

July 2, 2026