



FLY ASH TEST REPORT

Sample from : Hokuden Fly Ash
Average Analysis: August 2026
Test Report Number Hokuden-9-26_F

Chemical Analysis

Silicon Dioxide (SiO_2)	63.6 %
Aluminum Oxide (Al_2O_3)	23.5 %
Iron Oxide (Fe_2O_3)	4.6 %
Total (SiO_2) + (Al_2O_3) + (Fe_2O_3)	91.7 %
Sulphur Trioxide (SO_3)	0.1 %
Calcium Oxide (CaO)	0.9 %
Magnesium Oxide	0.6 %
Moisture Content	0.12 %
Loss on Ignition	2.55 %
Available Alkalies as Equivalent Na_2O	0.55 %

Physical Analysis

Fineness Retained on 45 μm (No. 325 Sieve)	16.6 %
Strength Activity Index with Portland Cement	
% of Control at 28 Days (<i>previous month's result</i>)	87 %
Water Requirement, Percent of Control	96 %
Density	2.29 g/cm^3
Density, Variation from Average	0.20 %
Fineness 45 μm Sieve, Variation from Average	1.10 %

We hereby certify that the composite fly ash sample above meets the chemical, physical and testing frequency requirements of ASTM C618 for Type F Fly Ash.

* Tested at CCIL, ASTM C1077 and AASHTO R18 Accredited Laboratory

Rob Shogren, P.Eng, Ph.D.
Technical Director
Amrize